

# TRITOSIL H10 PU

## ADVANCED ONE-COMPONENT POLYURETHANE SEALANT

### DESCRIPTION

Tritosil H10 PU is a one component, gun-grade, Non-sag, moisture-cure polyurethane sealant designed to skin and cure rapidly. This high performance product is designed with outstanding UV resistance and long term durability.

### USES

- Sealant is designed to seal concrete construction joints.
- To seal waterproof rivet seams and roof rails.
- To seal perimeter joints around windows and doors.
- Sealing corner moldings, fabricated roof-lap seams, bumper assemblies and body-to-cab joints in motor homes.
- Sealing door hinges, skylights and pot holes.
- Sealing Air conditioning equipment, flashing and gutters.

### FEATURES

- 1.Paintable
- 2.Single component & convenient packing
- 3.Excellent adhesion without priming
- 4.Highly resistant to sea water, diluted acids and alkalis.
- 5.Odourless
- 6.UV resistant/ fast curing
- 7.Low VOC

### ADVANTAGES

- Accommodates  $\pm 25\%$  joint movement
- Permanently flexible, excellent weatherability
- Easy to gun, Easy to tool
- Cures to a tough, durable, elastic consistency with excellent cut and tear resistance
- Paintable, non-sticky after cure

### STANDARDS

Tritosil H10 PU meets or exceeds the requirements of the following specifications:  
ASTM C 920 Type S, Grade NS, Class 25.

### TECHNICAL SPECIFICATION

Physical Properties	Test Method	Typical Value
Specific Gravity @ 25°C, g/ml	ASTM D1475	1.15 $\pm$ 0.05
Skin Over Time @ 25°C, Minutes	-	10 - 35
Flow (sag or slump)	ASTM C639	Non Sag
Shrinkage,%	-	<5
VOC, (g/L)	USEPA Method 24	<25
Tensile Strength (N/mm <sup>2</sup> )	ASTM D412	1.3
Elongation at break, %	ASTM D412	>300
Hardness : Shore A	ASTM D2240	30 $\pm$ 3
Movement Capability, %	ASTM C719	$\pm$ 25
Peel Strength (N), concrete	ASTM C794	>30
Effects of Accelerated Ageing @ 300 hrs. UV exposure	ASTM C793	No deterioration
Application Temperature (°C)	-	+5 to + 40
Composition	-	Silane Terminated Polyurethane

## PACKAGING

600ml sausage, 20 sausages per carton

## COLORS

White, Off-white, Grey, and Black. For other colour please contact local Triton representative

## EXPANSION JOINT DESIGN

Tritosil H10 PU may be used in any joint designed in accordance with accepted architectural/engineering practices. Joint width should be at least 4 times anticipated movement, and not less than (5mm).

While applied on an expansion joint the depth (D) of the sealant should be equal to the width (W) of the joints that are less than 10mm wide. For wider joints, width to depth ratio should be 2 : 1.

The maximum width of the joint on which Tritosil H10 PU can be applied is 25mm.

Meter per 600 ml

Joint Width (mm)	10	12	15	20	25
Joint Depth (mm)	6	8	8	10	12
Joint Length (m)/600 ml	10	6.2	5	3	2

## JOINT BACKING

Closed cell polyethylene backer rod is recommended as joint backing to control sealant depth and to ensure intimate contact of sealant with joint walls when tooling. Where depth of joint is insufficient for the use of backer rod, an adhesive backed polyethylene tape (bond breaker tape) should be used to prevent three-sided adhesion. All backing should be dry at time of sealant application. Avoid using sharp tools.

## YIELD

The following formula is an approximate guideline to calculate foreseen yield for a standard 600ml sausage of Tritosil H10 PU.

$$L = 600 / (W \times D)$$

Where: L = Length of sealant in metres obtained per cartridge.

D = Depth of the joint in mm

W = Width of the joint in mm

## APPLICATION DETAILS

### SUBSTRATE PREPARATION

Surfaces must be sound, clean, and dry. All release agents, dust, loose mortar, laitance, paints, or other loose particles must be removed. This can be accomplished with a thorough wire brushing, sanding, or solvent washing, depending on the contamination. Triton recommends that surface temperatures be below 40°C at the time the sealant is applied.

### APPLICATION

Tritosil H10 PU is easy to apply with conventional caulking equipment. Ensure that the backer rod is friction fitted properly. Mask the sides of the joint with masking tape prior to filling for a cleaner finish. Fill the joint completely with a proper width-to-depth ratio and tool to ensure intimate contact of sealant with joint walls. Dry tooling is always preferred, although xylene can be used in limited amounts to slick the spatula if needed following the initial dry tooling.

## PRIMING

Tritosil H10 PU typically adheres to common construction substrates without primers; however, due to the variability of substrate finishes available, where deemed necessary, use Tritosil Prime PA mockup or field adhesion test can be performed on the actual materials being used on the job to verify the need for a primer.

## FOR OPTIMUM PERFORMANCE

- In cool or cold weather, store container at room temperature for at least 24 hours before using.
- Tritosil H10 PU can adhere to other residual sealants in restoration applications. For best results always clean the joint as advised in the Surface Preparation section of this data guide. A product field adhesion test for Tritosil H10 PU within the specific application is always recommended to confirm adhesion and suitability of the application.
- When using Tritosil H10 PU in a traffic-bearing horizontal joint, use a firmer joint backing, such as neoprene rod or polyethylene foam block, and recess the surface of sealant (3mm - 6mm).
- Pursuant to accepted industry standards and practices, using rigid paints and/or coatings over flexible sealants can result in a loss of adhesion of the applied paint and/or coating, due to the potential movement of the sealant however, should painting and/or coating be desired it is required that the applicator of the paint and/or coating conduct on-site testing to determine compatibility and adhesion.
- Proper application is the responsibility of the user. Field visits by Triton personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

### Note:

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control. Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields. Information on this datasheet is subject to change without notice and should not be used for writing specification. For additional information on specific applications, please contact Triton Middle East, LLC. The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet, or any verbal advice given, unless there is a case of willful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product. Triton reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned copies of which will be supplied on request.

Product of:



## CLEAN UP

Excess sealant and smears adjacent to the joint interface can be carefully removed with xylene or mineral spirits before the sealant cures. Any utensils used for tooling can also be cleaned with xylene or mineral spirits.

## LIMITATIONS

- Do not apply over damp or contaminated surfaces.
- Do not use Tritosil H10 PU as a structural (load transferring) sealant

## STORAGE AND SHELF LIFE

Tritosil H10 PU has a shelf life of 12 months when stored in tightly closed original casks, in a dry place at a temperature between +5°C and +25°C

## CURING TIME

Tritosil H10 PU generally cures at a rate of 2mm per day at 25°C and 50% relative humidity. Lower temperatures and humidity will extend curing time.

## HEALTH AND SAFETY

Use only with adequate ventilation. Prevent contact with skin, eyes and clothing. Wash thoroughly after handling. Avoid breathing vapors. DO NOT take internally. Use impervious gloves, eye protection if the TLV is exceeded or used in a poorly ventilated area. Always utilize the accompanying SDS for information on Personal Protective Equipment (PPE) and health Hazards.

Factory address

TRITON Middle East LLC  
P. O. Box 3350,  
Umm Al Quwain, U. A. E.  
Tel.: + 971 6 767 23 27  
Fax.: + 971 6 767 23 28  
E-mail: info@triton.me  
Web.: www.triton.me